



Plastic Welder™

Description: Toughened structural adhesive, after curing, produces superior strength to load-bearing bonds to engineered plastics.

Intended Use: Bond: PVC, fiberglass, ABS, FRT, PBT, PPO, PCBB, Metton®, Lomod®, Valox®, Noryl®, GTX, Minlon®, epoxy, RIM urethane, galvanized metal, wood, poorly prepared surfaces, and where outdoor weathering or solvent exposure is anticipated.

Product features:
Minimal surface preparation
Room temperature cure
1:1 mix ratio
Rapid fixture in thin set
Thixotropic/non-sagging

Limitations:

Typical Physical Properties: *Technical data should be considered representative or typical only and should not be used for specification purposes.*

Cured 7 days @ 75° F

T-peel	35-40 pli
Impact Resistance	22 ft.lb./in.[2]
Tensile Elongation	15-25%
Shore Hardness	78 Shore D
Gap-Fill	0.125 in.
% Solids by Volume	100
Adhesive Tensile Lap Shear[ABS]	1,300 psi
Adhesive Tensile Lap Shear[GBS]	3,500 psi
Adhesive Tensile Lap Shear[Polycarb]	1,400 psi
Specific Volume	28.1 in[3]/lb.

TESTS CONDUCTED

Impact Resistance ASTM D 950
T-Peel Strength ASTM D 1876
Cured Hardness Shore D ASTM D 2240
Adhesive Tensile Shear ASTM D 1002

Uncured

Color	Off White
Viscosity	Adhesive: 55,000 cps; Activator: 50,000 cps
Weight	Adhesive: 8.4 lbs./gal.; Activator: 8.00 lbs./gal.
Mixed Viscosity	50,000 cps
Mix Ratio by Volume	1:1
Mix Ratio by Weight	1:1
Mixed Density	8.20lbs./gal. / .98gm/cc
Flashpoint	51°F
Working Time	4-6 min. @ 72°F,
Fixture Time	10-15 min. @ 72°F, 22°C
Functional Cure	3/4 - 1 hr.
Full Cure	24 hrs.
Service Temperature	-67°F to 250°F

Surface Preparation: Clean surface by solvent-wiping any deposits of heavy grease, oil, dirt, or other contaminants. Surface can also be cleaned with industrial cleaning equipment such as vapor phase degreasers or hot aqueous baths. If working with metal, abrade or roughen the surface to significantly increase the microscopic bond area and optimize the bond strength.

Mixing Instructions: ---- Proper homogenous mixing of resin and hardener is essential for the curing and development of stated strengths. ----

- 25 ML DEV-TUBE
1. Squeeze material into a small container the size of an ashtray.
 2. Using mixing stick included on Dev-tube handle, vigorously mix components for one (1) minute.
 3. Immediately apply to substrate.

- 35ML/50 ML/380ML/400 ML CARTRIDGES
1. Attach cartridge to Mark 5 dispensing system.
 2. Open tip.

3. Burp cartridge by squeezing out some material until both sides are uniform (ensures no air bubbles are present during mixing).
4. Attach mix nozzle to end of cartridge.
5. Apply to substrate.

Application Instructions:

1. Apply mixed product directly to one surface in an even film or as a bead.
2. Assemble with mating part within recommended working time.
3. Apply firm pressure between mating parts to minimize any gap and ensure good contact (a small fillet of product should flow out the edges to display adequate gap fill.)
4. Bond line thickness of mixed adhesive should be @ .015"-.030" for optimum adhesion.

For very large gaps:

1. Apply product to both surfaces
2. Spread to cover entire area OR make a bead pattern to allow flow throughout the joint

Let bonded assemblies stand for recommended functional cure time prior to handling.

ADDITIONAL PRODUCT INFORMATION:

- Can withstand processing forces
- Do not drop, shock load, or heavily load
- Intermittent exposure to temperatures above 250°F do not reduce performance characteristics

STAINLESS STEEL AND ALUMINUM APPLICATIONS:

Apply Devcon Metal Prep 90 to prime and condition aluminum and stainless steel surfaces prior to using Plastic Welder. Metal Prep 90 is fast drying at ambient temperatures. Plastic Welder can be applied within minutes of its use. Overlap shear strength will improve 30-40% if Metal Prep 90 is used.

Storage:

Store in a cool, dry place.

Compliances:

None

Chemical Resistance:

Chemical resistance is calculated with a 7 day, room temp. cure (30 days immersion) @ 75°F

Acetic (Dilute) 10%	Excellent	Sulfuric 10%	Excellent
Ammonia	Very good		
Cutting Oil	Excellent		
Glycols/Antifreeze	Excellent		
Hydrochloric 10%	Fair		
Mineral Spirits	Excellent		
Motor Oil	Excellent		
Sodium Hydroxide 10%	Very good		

Precautions:

Please refer to the appropriate material safety data sheet (MSDS) prior to using this product.

For technical assistance, please call 1-800-933-8266

FOR INDUSTRIAL USE ONLY

Warranty:

Devcon will replace any material found to be defective. Because the storage, handling and application of this material is beyond our control, we can accept no liability for the results obtained.

Disclaimer:

All information on this data sheet is based on laboratory testing and is not intended for design purposes. ITW Devcon makes no representations or warranties of any kind concerning this data.

Order Information:

14320 47 ml DevPak
 14385 400 ml cartridge
 14300 25 ml DevTube
 14330 2 liter kit